

Product 01468010 2-comp. EP advanced resin-based coating, water based, coloured, gloss

## 1 General Data

### Fields of application

FLOORFINDER EP-S6801 is designed for use as a protective coating on concrete, block work, brick, steel, timber and laminate surfaces. It is recommended for use in situations subject to water condensation, high water pressure cleaning and vehicular traffic. It is also recommended for use as a wall coating in food and pharmaceutical manufacturing environments.

### Product description

FLOORFINDER EP-S6801 is a coloured, two-component, water vapour permeable, advanced resin-based coating with low/no odour and low emission of VOC (volatile organic compounds). It provides a hard wearing and impervious surface that is easily cleaned and highly resistant to fuels and lubricants as well as most solvents and many chemicals.

Compared to traditional epoxy systems this product shows good indoor colour stability and weather resistance.

### Features & Benefits

- **Chemical resistant** – to petroleum oils, solvents and commercial cleaning agents
- **High solids** – durable; higher DFT
- **Low VOC emission**
- **High water vapour permeability** – does not blister in situation subject to hydrostatic pressure
- **Good adhesion** to concrete and most building material and other coating or topping systems
- **Water impermeable** – waterproof
- **Low / no odour** – does not taint food
- **Solvent free** – non-flammable, non-toxic and environmentally friendly
- **Easy application** – by roller or airless spray for fast installation

### FLOORFINDER systems

FLOORFINDER EP-S6801 is sealer for the FLOORFINDER systems:

FLOORFINDER **PERM**  
 FLOORFINDER **PERM SR**  
 FLOORFINDER **PERM DECK**  
 FLOORFINDER **PERM protective**

#### Manufacturer:

Floorfinder Asia Sdn. Bhd., No. 28, Lorong Sungai Puloh 1A/KU6, Jalan Sungai Puloh, Batu 5 3/4, Kapar, 42100 Klang, Selangor Darul Ehsan, Malaysia, tel: +603 3290 7644, email: [info@floorfinderasia.com](mailto:info@floorfinderasia.com), [www.floorfinderasia.com](http://www.floorfinderasia.com) – A division of VIACOR VISION AG, SWITZERLAND

#### (A) Technical data

##### Liquid mixture (A+B)

1. Solids content	74 %
2. Density (25°C)	1.37 g/cm <sup>3</sup>
3. Viscosity (25°C)	1200–1600 mPas
4. Packaging size	22 kg (17.8 kg A + 4.2 kg B)
5. Colours	FLOORFINDER standard
6. Shelf life	12 months in closed original container
7. Storage	Dry and frost-free at 10–30°C, avoid direct sunlight

#### (B) Technical data

##### Cured material

1. Adhesive strength (DIN ISO 4624)	> 1.5 N/mm <sup>2</sup> (concrete failure)
-------------------------------------	---

### Care and maintenance

The lifespan & performance of your resin floor can be extended considerably by adopting a regular cleaning and care programme. We recommend the use of an alkaline based cleaning agent.

### Technical support

For system build up possibilities and detailed information relating to the laying of FLOORFINDER products, please refer to the FLOORFINDER System Planner or contact Floorfinder Asia Sdn. Bhd. directly.

Tel: +603 3290 7644

e-mail: [info@floorfinderasia.com](mailto:info@floorfinderasia.com)

**Product 01468010** 2-comp. EP advanced resin-based coating, water based, coloured, gloss

## 2 Application method

### Substrate preparation

The substrate must be firm, clean, dry and have a pull-off strength of 1.5 N/mm<sup>2</sup> minimum.

Concrete substrate should have no ponded water. The moisture content in the substrate is not relevant.

The product can be used on fresh concrete as a curing compound (water will stay in concrete long enough for curing of concrete to gain the desired strength).

Repair imperfections (holes and cracks) with an epoxy patching compound such as FLOORFINDER EP-T703 where necessary.

Remove surface laitance, contaminants, coating, curing compound and all weak and loose materials.

Prepare substrate by Captive Shot Blasting or Diamond Grinding to provide the appropriate surface profile for optimum mechanical interlocking.

For the newly laid laminate, no surface preparation is required if less than 24 hours old. A light sanding is required if the laminate surface is over 24 hours old.

### Application

Before starting the application, the material temperature must be close to site conditions.

Mix Component A for 2-3 minutes.

Empty contents of component B (Hardener) into component A (Base Resin). Mix with a suitable mixer at a speed of 500 rpm to avoid incorporating excessive air into the mix. Mix for 2-3 minutes.

Transfer the mixture into another clean container and mix for 1-2 minutes.

It is recommended to dilute the product with maximum 3% water before use.

Spread the mixed product onto the surface with a squeegee or trowel and back roll with a short nap roller in a criss-cross manner.

It is recommended to apply a seal coat of FLOORFINDER EP-S684 or polymer wax to seal the surface to avoid dirt pick-up.

### (C) Technical data

#### Liquid mixture (A+B)

1. Mixing ratio A : B	100 : 23.6
2. Working time	approx. 25 min. (25°C) approx. 20 min. (30°C)
3. Application temperature	10 – 30°C (min. 3°C above dew point)
4. Material consumption on smooth surfaces (diluted) on broadcasted surfaces	250 – 300 g/m <sup>2</sup> 400 – 600 g/m <sup>2</sup>
5. Following coating (25°C)	within 24 hours
6. Cure time to withstand: Foot traffic (25°C) High pressure cleaning (25°C) Water immersion (25°C)	after 6 - 8 hours after 3 days after 7 days

Do not apply too thick and do not allow any puddling. Provide good ventilation to ensure that the relative air humidity does not exceed 80% during application and curing as it will inhibit evaporation of water and affect cure.

Apply FLOORFINDER EP-S6801 a second time if coverage is insufficient.

For cleaning of tools and other contaminations use water.

### Overcoating

The second coat can be applied within 24 hours without grinding. If longer, the surface has to be grinded before over-coating.

#### Manufacturer:

Floorfinder Asia Sdn. Bhd., No. 28, Lorong Sungai Puloh 1A/KU6, Jalan Sungai Puloh, Batu 5 3/4, Kapar, 42100 Klang, Selangor Darul Ehsan, Malaysia, tel: +603 3290 7644, email: [info@floorfinderasia.com](mailto:info@floorfinderasia.com), [www.floorfinderasia.com](http://www.floorfinderasia.com) – A division of VIACOR VISION AG, SWITZERLAND

Product 01468010 2-comp. EP advanced resin-based coating, water based, coloured, gloss

### 3 Further information

#### CE-Mark



##### CE-Mark according to EN 13813

EN 13813: 2003-01, Screed material and floor screeds - Screed materials - Properties and requirements is the basis for requirements for floor screeds used in indoor flooring constructions. Resin coatings and sealer are also subject to this norm.

Details see CE-conformity mark and conformity declaration.

#### Warnings and precautions

Information relating to the safe handling of this product can be found in the Material Safety Data Sheet. Local regulations concerning the safe handling of epoxy resin-based coating materials must be observed.

Suitable protective clothing including suitable eye protection must be worn.

#### Disclaimer

All information in this technical data sheet is based on our current knowledge and experience. This does not release the applicator from performing their own tests as many application factors, beyond our control, affect the application of our product. No guarantee of characteristics or suitability for a special purpose can be derived from this information. All present data, descriptions, drawings, photos, ratios, weights etc. are subject to change without prior notice and do not represent contracted characteristics of the product.

Due to different materials, sub-bases and working conditions, no guarantee of an application result or any liability claims can be derived from these details or from an unwritten technical advice except for liability claims based on:

- damage to life, body or health resulting from a negligent violation of obligations or a deliberate or negligent violation of obligation of a legal representative or assistant and

- if we are charged with intention or gross negligence.

The user has to test the products for their intended use. The user is responsible for following existing laws and orders and for observing third party trademark rights.

As all Floorfinder data sheets are updated on a regular basis it is the users responsibility to obtain the most recent issue (see [www.floorfinderasia.com](http://www.floorfinderasia.com)).

#### Manufacturer:

Floorfinder Asia Sdn. Bhd., No. 28, Lorong Sungai Puloh 1A/KU6, Jalan Sungai Puloh, Batu 5 3/4, Kapar, 42100 Klang, Selangor Darul Ehsan, Malaysia, tel: +603 3290 7644, email: [info@floorfinderasia.com](mailto:info@floorfinderasia.com), [www.floorfinderasia.com](http://www.floorfinderasia.com) – A division of VIACOR VISION AG, SWITZERLAND